

FINAL REPORT

CERTIFICATE No.: 26470



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Marulan Quicklime Fines - Despatch Composite
PRODUCED AT: Boral Cement Limited Marulan
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: LDQLF2404556
DATE SAMPLED: for date ending 9/18/2024

PROPERTY	RESULT
Chemical Composition (AS 4489.5.1)	
CaO	92.3 %
MgO	0.9 %
Al ₂ O ₃	0.4 %
SiO ₂	1.1 %
K ₂ O	0.1 %
Fe ₂ O ₃	0.3 %
LOI (AS 4489.7.1)	4.6 %
ALI as CaO (AS 4489.6.1)	87.5 %
Slaking (AS 4489.3.1)	
Temperature Rise at 30 s	22.5 °C
Temperature Rise at 3 min	41.5 °C
Total Temperature Rise	44.5 °C
Total Active Slaking Time	7.0 mins
Residue on Slaking	0.34 %
Particle Size Distribution * (AS 1141.11.1)	
< 4.75 mm	100 %
< 2.36 mm	100 %
< 1.18 mm	98 %
< 600 µm	93 %

REMARKS

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

* Samples are not washed.



Accredited for compliance with ISO/IEC 17025 - Testing

Jason Nairn
National Technical Manager