## **FINAL REPORT**

CERTIFICATE No.: 26390



Boral Cement Limited ABN 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Shrinkage Limited Cement

PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory

SAMPLE IDENTIFICATION: MDDSL2404015

DATE DESPATCHED: 9/2/2024

| ROPERTY                       |               | REQUIREM | ENTS OF AS 3972    |                    | RESULT                 |
|-------------------------------|---------------|----------|--------------------|--------------------|------------------------|
| Compressive Strength (AS      | /NZS 2350.11) |          |                    |                    |                        |
| 3 Day                         |               |          |                    |                    | 37.1 MPa               |
| 7 Day                         |               | Minimum  | 35 MPa             |                    | 48.6 MPa               |
| 28 Day                        |               | Minimum  | 45 MPa             |                    | 59.8 MPa               |
| Setting Time (AS/NZS 235      | 50.4)         |          |                    |                    |                        |
| Initial                       |               | Minimum  | 45 mins            |                    | 135 mins               |
| Final                         |               | Maximum  | 600 mins           |                    | 165 mins               |
| Soundness (AS/NZS 2350.5)     |               | Maximum  | 5 mm               |                    | 0 mm                   |
| SO <sub>3</sub> (AS 2350.2)   |               | Maximum  | 3.5 %              |                    | 2.6 %                  |
| CI (AS 2350.2)                |               | Maximum  | 0.10 %             |                    | 0.01 %                 |
| Shrinkage (AS 2350.13)        |               |          |                    |                    |                        |
| 28 Day Mean                   |               | Maximum  | 750 μstrain        |                    | 620 μstrair            |
| OTHER REPORTABLE PI           | ROPERTIES     |          | PHYSICAL           |                    |                        |
| K <sub>2</sub> O (AS 2350.2)  | 0.68 %        |          | Normal Consistency | (AS/NZS 2350.3)    | 27.5 %                 |
| Na <sub>2</sub> O (AS 2350.2) | 0.08 %        |          | Fineness Index     | (AS/NZS 2350.8)    | 385 m <sup>2</sup> /kg |
| LOI (AS 2350.2)               | 4.0 %         |          | i illorioss iridox | (7.07.1120 2000.0) | 555 III /kg            |

## **REMARKS**

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type SL (GP) cement with up to 7.5% limestone mineral addition.

Shaller

Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531

Jason Nairn National Technical Manager Date of Issue: 10/10/2024

Page 1 of 1